

## OK Tigrod 12.62

A tripple desoxidized copper coated rod designed for GTAW of mild and fine grained structural- and pressure vessel steels as well as ship building steels. The rod is capable of producing high quality welds in semi-killed and rimmed steel as well as steel of various carbon levels. Because of added desoxidants, Al-Ti-Zr, the rod can also be used for welding steels with a rusty or dirty surface, without any sacrifice of weld quality.

<b>Classifications</b>	SFA/AWS A5.18 : ER70S-2 EN ISO 636-A : W2Ti
------------------------	--

<b>Alloy Type</b>	Carbon-manganese steel
<b>Shielding Gas</b>	I1 (EN ISO 14175)

### Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
<b>Ar (I1) EN</b>			
As Welded	570 MPa (83 ksi)	625 MPa (91 ksi)	26 %

### Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
<b>100% Ar</b>		

### Typical Wire Composition %

C	Mn	Si	S	P	Ni	Cr	Mo	V	Al
0.06	1.1	0.6	0.009	0.008	0.03	0.12	0.01	0.01	0.12

### Typical Wire Composition %

Cu	Ti+Zr
0.05	0.13