

OK Autrod NiCrMo-13

A continuous solid Ni-Cr-Mo electrode for welding of high alloyed Ni-base materials, 9 %Ni steel and super austenitic steels of type 20Cr-25Ni with 4-6 % Mo. Can also be used for welding carbon steel to Ni base steel. The weld metal has a very good toughness and is corrosion resistant over a wide range of applications in oxidizing and reducing media.

Classifications Wire Electrode	SFA/AWS A5.14 : ERNiCrMo-13 EN ISO 18274 : S Ni 6059 (NiCr23Mo16)
Approvals	VdTÜV 12662 (MV)

Approvals are based on factory location. Please contact ESAB for more information.

Alloy Type	Alloyed nickel (Ni + 23 % Cr + 16 % Mo)
-------------------	---

Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
As Welded	500 MPa (73 ksi)	750 MPa (109 ksi)	40 %
As Welded	500 MPa (73 ksi)	700 MPa (102 ksi)	42 %

Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
As Welded	-110 °C (-166 °F)	120 J (89 ft-lb)

Typical Weld Metal Analysis %

C	Mn	Si	S	P	Cr	Mo	Al	Co	Fe
0.002	0.15	0.03	0.002	0.003	22.7	15.4	0.15	0.02	0.5

Typical Wire Composition %

C	Mn	Si	Ni	Cr	Mo	Al	Fe
0.01	0.2	0.1	bal	23.0	16.0	0.3	1.0

Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
1.0 mm (0.040 in.)	100-200 A	21-27 V	6.0-13.0 m/min (236-512 in./min)	2.5-5.5 kg/h (5.5-12. lb/h)
1.2 mm (0.047 in.)	160-280 A	24-30 V	6.0-10.0 m/min (236-394 in./min)	3.6-6.0 kg/h (7.9-13. lb/h)
1.6 mm (1/16 in.)	200-350 A	25-32 V	4.0-8.0 m/min (157-315 in./min)	4.3-8.6 kg/h (9.5-19. lb/h)