

## OK NiCrMo-13



OK NiCrMo-13 is suitable for welding Ni base materials such as Alloy 59, Hasteloy C-276, Inconel 625 and Incoloy 825. It can also be used for welding superaustenitic steels type AISI/ASTM S31254 and S32654.

The weld metal provides very good resistance against pitting- and chloride ion stress corrosion cracking.

<b>Classifications</b>	SFA/AWS A5.11 : ENiCrMo-13 EN ISO 14172 : E Ni 6059 (NiCr23Mo16)
------------------------	---

<b>Welding Current</b>	DC+
<b>Ferrite Content</b>	FN 0
<b>Alloy Type</b>	Ni-based CrMo
<b>Coating Type</b>	Basic

### Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
<b>ISO</b>			
As Welded	430 MPa (62 ksi)	770 MPa (112 ksi)	40 %

### Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
<b>ISO</b>		
As Welded	-60 °C (-76 °F)	70 J (52 ft-lb)
As Welded	-196 °C (-321 °F)	60 J (44 ft-lb)

### Typical Weld Metal Analysis %

C	Mn	Si	Ni	Cr	Mo	Fe
0.013	0.17	0.16	61	22.6	15.2	0.6

### Deposition Data

Diameter	Current	Voltage	Number of electrodes/ kg weld metal	Burn-off Time/ Electrode	Deposition Efficiency %	Deposition Rate @ 90% I max
2.5 x 300.0 mm (0.098 x 11.8 in.)	50-70 A	25 V	90	50 sec	60 %	0.8 kg/h (1.8 lb/h)
3.2 x 350.0 mm (1/8 x 13.8 in.)	60-90 A	25 V	47	63 sec	62 %	1.2 kg/h (2.6 lb/h)
4.0 x 350.0 mm (5/32 x 13.8 in.)	80-120 A	27 V	31	81 sec	62 %	1.4 kg/h (3.1 lb/h)