



OK Autrod 410NiMo

A continuous solid corrosion resisting "410NiMo" type alloyed with 13 % Cr, 4.5 % Ni and 0.5 % Mo.

This alloy is used for welding of similar martensitic and martensitic-ferritic steels in different applications such as for example hydro-turbines. OK Autrod 410NiMo can be used in combination with OK Flux 10.93.

Classifications Wire Electrode	EN ISO 14343-A : S 13 4
---------------------------------------	-------------------------

Alloy Type	Martensitic-ferritic (12 % Cr - 4.5 % Ni - 0.5 % Mo)
-------------------	--

Typical Wire Composition %						
C	Mn	Si	Ni	Cr	Mo	Cu
0.02	0.5	0.4	4.2	12.4	0.6	0.1